



# EUCOWELD 2.0

## Latex Bonding Agent for Concrete Repairs and Toppings

### Description

EUCOWELD 2.0 is a liquid latex bonding agent for cement-based repair mortars and concrete. EUCOWELD 2.0 has a long open time, and repair materials can be placed either after it has dried, or while it is still wet. This bonding agent represents a new generation of easy-to-use latex, which exhibits drastically improved performance and stability in comparison to the typical re-wettable ethylene vinyl acetate (EVA) bonding agents currently available. EUCOWELD 2.0 is a unique, non-EVA based latex that utilizes reactive chemistry for bonding, rather than depending on the moisture content of the repair material.

### Primary Applications

- Repairing concrete with cement-based mortars
- Concrete overlays and toppings
- Interior or exterior use
- Repairs that will be frequently wet or submerged after curing

### Features/Benefits

- Excellent bond strengths
- Repair materials can be applied wet-on-wet, or after it has dried
- Easy to use - applied to surface straight from container
- Long open time

### Technical Information

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Physical Property	Value
Unit Weight, Specific Gravity	8.4 lbs/gal, 1.01
VOC Content	< 5 g/L
Viscosity	100 cp

Engineering Property	Value
Tack Free Time	2 to 3 hours
Direct Tension Bond Strength, ASTM C1583	24 hours: 340 psi (2.3 MPa) 7 days: 370 psi (2.6 MPa)
Slant Shear Bond Strength, ASTM C882	14 days, dry conditioned: 2,730 psi (18.8 MPa) 14 days, wet conditioned: 2,760 psi (19.0 MPa)

### Packaging

EUCOWELD 2.0 is packaged in 5 gal (18.9 L) pails and in cases of 1 gal (3.8 L) jugs (6 jugs per case).

### Shelf Life

1 year in original, unopened container

### Specifications/Compliances

ASTM C1059, Type II

### Coverage

150 to 250 ft<sup>2</sup>/gal (4.91 to 6.14 m<sup>2</sup>/L)

## Directions for Use

**Surface Preparation:** Concrete surface must be clean, dry and structurally sound. The substrate must also be free of all curing compounds, form release agents and any other contaminants, which may prevent the proper adhesion of EUCOWELD 2.0. When using EUCOWELD 2.0 to bond Euclid Chemical cementitious repair mortars, please refer to the technical data sheet for the repair mortar to find the concrete surface profile (CSP) requirements. After surface preparation is complete, rinse thoroughly with potable water. Allow the concrete to dry before applying EUCOWELD 2.0.

**Application:** Stir EUCOWELD 2.0 thoroughly before use. Do not dilute. For hand application, dampen brushes or rollers before use and shake out excess water. For larger areas or faster applications, use airless spray equipment or an industrial pump-up sprayer with a fan tip nozzle. Hold spray nozzle 12 to 18 inches (30 to 46 cm) from the surface and apply EUCOWELD 2.0 using a cross coat technique consisting of a horizontal pass followed by a vertical pass. Extremely porous surfaces may require two coats of EUCOWELD 2.0.

EUCOWELD 2.0 may be allowed to dry before placing repair mortars, concrete, or toppings, or the repair materials may be placed in a "wet on wet" fashion, immediately after application of EUCOWELD 2.0. EUCOWELD 2.0 will dry in approximately two to three hours depending on the temperature and humidity. If more than 7 days pass between EUCOWELD 2.0 application and placement of the concrete, topping, or mortar, the surface must be abraded to remove existing product, and EUCOWELD 2.0 must be re-applied. During the product's open time, regardless of length of time, the surface must be protected from dust, dirt, foot traffic, and any other sources of contamination or abrasion prior to application of the concrete, topping, or mortar. Any dust, dirt, or other contaminants will severely affect bond strength of the concrete, topping, or mortar.

## Clean-Up

Clean tools and equipment with soap and water immediately following use. Clean drips and over-spray with water while still wet. Dried EUCOWELD 2.0 may require mechanical abrasion for removal.

## Precautions/Limitations

- Do not dilute EUCOWELD 2.0.
- Keep from freezing.
- Do not apply to frozen or frost filled surfaces.
- Surface and ambient temperature during application must be 40°F (4°C) and rising.
- Store at temperatures between 40°F to 90°F (4°C to 32°C).
- In all cases, consult the Safety Data Sheet before use.

Rev. 09.20

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.