

## TECHNICAL DATA SHEET

# AV-278 LOW VIS HYDRO™

## HYDROPHOBIC POLYURETHANE GROUT

### DESCRIPTION

**AV-278 Low Vis Hydro™** is a moisture activated MDI-based polyurethane resin whose chemical reaction is catalyzed by mixing **AV-279 Low Vis Accel™** with AV-278. Injected as a single component, **AV-278** is low viscosity and designed with soil permeation in mind. It penetrates with very high expansion to fill voids, stops active or potential water leaks, and stabilizes soils. **AV-278** withstands wet/dry cycles, permeates well, and reacts with water to cure dense, closed-cell, impermeable and semi-rigid.

### APPLICATION

- Ground modification/slope stability for prevention of landslides, erosion, or any place where site conditions or project requirements dictate modification of the existing soil properties
- Fills voids on the exterior of below-grade structures
- Stops leaks in below-grade structures

### FEATURES AND BENEFITS

- Low viscosity allows for excellent permeation
- Free rise expands 4,000-6,000%
- Solvent-free
- Pumped as a single component
- Controllable reaction time by adjusting **AV-279** volume
- Withstands wet/dry cycles

### GROUTING TECHNIQUES

- Probe Grouting
- Curtain Grouting
- Pressure Injection

### HOW IT WORKS

**AV-278 Low Vis Hydro** uncured resin must be injected into a confined space. Fill the space at least halfway with unreacted resin. The resin will react with moisture to form a resilient seal accomplished by three mechanisms: the resin seeks out water in the space and adheres to the surface, then begins to expand in the confined space to form a tight, high density compression seal, while the network of compressed grout material within all the cracks/joints forms a mechanical lock.

### CATALYST

- **AV-279** Low Vis Accel – 78 fl. oz. container (approx. 4.42 lbs.)

### PACKAGING - Product packaged by weight based on specific gravity.

Drum	Net Wt. 484 lbs. (220 kg)
Pail	Net Wt. 44 lbs. (20 kg)
Gallon	Net Wt. 8 lbs. (3.6 kg)
Dual Cartridge	AV-278 – 25.3 fl. oz. (750 ml) AV-279 – 2.5 fl. oz. (75 ml)
Barrier Cartridge	AV-278 – 8 fl. oz. (236 ml) AV-279 – 2 fl. oz. (59 ml)

### SHIPPING

- Motor Class 55
- Non-Hazardous
- Air freight available

### CLEANING PRODUCTS

- **AV-208** Technical Grade Acetone™ (CAS# 67-64-1) – removes moisture from equipment
- **AV-222** Cleaner™ (Proprietary Blend) – removes cured resin from equipment
- **AV-284** Pump Wash™ (Proprietary Blend) – removes uncured resin from pump and hose

### PROPERTIES\*

#### AV-278 – UNCURED

Appearance:	Brown resin
Viscosity:	25 – 100 cP @ 72°F (22°C)
Flash Point:	244.4°F (118°C)
Specific Gravity:	1.171 @ 72°F (22°C) ± 3%
Density:	9.77 lbs./gal. ± 3% (1,171 kg/m <sup>3</sup> ± 3%)

#### AV-278 – CURED

Appearance:	Milky colored, rigid
Compressive Strength:	TBD
Toxicity:	Non-toxic

#### AV-279 Low Vis Hydro Accel

Appearance:	Light yellow liquid
Viscosity:	15-25 cP @ 72°F (22°C)
Flash Point:	>200°F (>93°C)
Specific Gravity:	0.986 @ 72°F (22°C) ± 3%
Density:	8.23 lb./gal. ± 3% (986 kg/m <sup>3</sup> ± 3%)

\*Laboratory Results

Temperature	Gel (Cure) Times for AV-278 Low Vis Hydro (Min:Sec)	
	Half Catalyst	Full Catalyst
40°F / 4°C	2:00	1:15
50°F / 10°C	1:43	1:05
60°F / 15°C	1:20	0:48
70°F / 21°C	1:05	0:40

### MIX PROCEDURE

Gently shake or stir container(s) before using. Depending on the desired reaction time, up to one container of **AV-279** Low Vis Accel can be used (see chart above). **Do not use more than one container of AV-279.** Mix thoroughly, but slowly, to avoid creating bubbles in the solution (air bubbles will turn into moisture). Perform the standard cup test with site water to determine the desired reaction time.

### PERFORMANCE

Flush equipment with **AV-208** before and after use to remove moisture and clean equipment. Performance will be influenced by site conditions. If site temperatures are low, heat the product to recommended operating temperatures of 60°F – 90°F (16°C – 32°C) and/or increase catalyst amount by 1% – 2%. Do not use open flame as a heat source. Excess amounts of **AV-279** may adversely affect performance. Because catalyzed resin will react to moisture from the air, use product soon after mixing for best results.

### SAFETY

Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The SDS is available by request or via online download at [avantigrout.com](http://avantigrout.com).



**AVANTI**  
Stop leaks. Stabilize soil.  
Control groundwater. **Permanently.**

Rev. 08.2022

## TECHNICAL DATA SHEET

# AV-278 LOW VIS HYDRO™

## HYDROPHOBIC POLYURETHANE GROUT

### STORAGE

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere.

### NOTICE

The data, information and statements contained herein are believed to be reliable but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. **NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE.** In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.